



**RUBBER
COATING
MANUFACTURING**

TECHNICAL DATA SHEET

RCM CLEARGUARD

PRODUCT CODE: CG001

COMPILED DATE: 21 JAN 25

REVISE DATE: 21 JAN 26

PRODUCT DISCRIPTION

General purpose Water Repellent for masonry and porous structures and surfaces

INTENDED APPLICATIONS

Waterproofing water repellent for unpainted plaster, face brick walls and porous surfaces. It can be applied as priming of exterior and interior walls, ceilings, gypsum board ,Skim surfaces and facias as well.

PRODUCT FEATURES

Easy to applicate and clean with no thinning
Environmentally friendly with no solvents
Low odour

TECHNICAL DATA

Appearance:	Milky, homogeneous emulation
Binder:	Styrene Acrylic Co Polymeric
Colour:	Various see catalogue
SG:	1,01 - 1,05
KU:	< 40 @23Deg C
pH:	7 - 8,4
Recommended WFT:	100 micron
VOC:	Low VOC

APPLICATION DIRECTIVE

Mixing and Thinning:	Single component, stir well before use. Do not dilute.
Coverage:	1 L per 8 square meter, dependant on: Substrate (Profile and porosity) and application.
Environment:	10 to 30 Dig C, Max R Humidity 85%
Drying time before overcoat:	1 Hours @23 Dig C, R Humidity 50%
Substrate:	Cleaned thoroughly, remove old unstable paint.

Treat all areas with primer if applicable.
Substrate must be dry.

TRANSPORTATION AND STORAGE

Transport: Classified as non-hazardous
Store: Store away from severe cold, heat and direct sun.

PACKAGING

Standard: 5L, 20L

SAFETY PRECAUTIONS

Although the product is non-hazardous, caution should be taken during application and storage. Keep container closed properly and away from children. Avoid contact with eyes, do not ingest. If ingested, drink plenty of water or milk, seek medical attention immediately. Refer to MSDS for complete information.

These recommendations are made as a result of testing and experience, it is believed to be true and in good faith. These directives do not imply any guarantee as the application and surface preparation methods is not within our control.



**RUBBER
COATING
TECHNOLOGIES**
WATER PROOFING AT IT'S BEST

MARIUS VAN DER WESTHUIZEN

Cell: 083 262 6432
Office: 041 484 1569
Email: marius@rubbercoating.co.za
Web: www.rubbercoating.co.za



**RUBBER
COATING
MANUFACTURING**
PTY LTD

ENVIRONMENTALLY SAFE, NON - HAZARDOUS PROTECTIVE COATINGS